

Water-Soluble Silicones

Bis-PEG-18 Methyl Ether Dimethyl Silane
Bis-PEG-8 (or higher) Dimethicone
Cetyl PEG/PPG-15/15 Butyl Ether Dimethicone
DEA PG-Propyl PEG/PPG-18/21 Dimethicone
Dimethicone Copolyol
Dimethicone PEG-X Phosphate
Dimethicone-PG Diethylmonium Chloride
Hydrolyzed Silk PG-Propyl Methylsilanediol
Crosspolymer
Hydrolyzed Wheat Protein Hydroxypropyl
Polysiloxane
Hydrolyzed Wheat Protein PG-Propyl Silanetriol
Lauryl Methicone Copolyol
PEG-12 Dimethicone
PEG-33 (and) PEG-8 Dimethicone (and) PEG-14
PEG-40/PPG-8 Methylaminopropyl/Hydropropyl
Dimethicone Copolymer
PEG-7 Amodimethicone
PEG-8 Disteramonium Chloride PG-Dimethicone
PEG-8-PG-Coco Glucoside Dimethicone
PEG-Modified Dimethicone
PEG/PPG-20/15 Dimethicone
Silicone Quaternium-8
Silicones with PEG or PPG listed before them

Slightly Water-Soluble Silicones

Amodimethicone
Behenoxy Dimethicone
Bis-Amino PEG/PPG-41/3 Aminoethyl PG-Propyl
Dimethicone
Bis-Aminopropyl Dimethicone
Cyclohexasiloxane
Cyclomethicone
Cyclopentasiloxane
Cyclotetrasiloxane
Hexamethyldisiloxane
Lauryl Methicone Copolyol
Lauryl PEG/PPG-18/18 Methicone
Octamethyl cyclotetrasiloxane

Silicone Quaternium-16
Silicone Quaternium-17
Silicone Quaternium-18
Silicone Quaternium-22
Stearoxy Dimethicone
Trimethylsilylamodimethicone

Insoluble Silicones

Bis-Cetearyl Amodimethicone
Bis-Hydroxy/Methoxy Amodimethicone
Bis-Phenylpropyl Dimethicone
Cetearyl Methicone
Cetyl Dimethicone
Di-Isostearoyl Trimethylolpropane Siloxy Silicate
Dimethicone
Dimethicone/Vinyldimethicone Crosspolymer
Dimethiconol
Diphenyl Dimethicone
Disiloxane
Hexamethyldisiloxane
PCA Dimethicone
Phenyl Trimethicone
Polysilicone-18 Cetyl Phosphate
Silicone Resin Spheres
Simethicone Stearoxy (or Stearyl) Dimethicone
Stearoxy Dimethicone
Stearyl Dimethicone
Trimethylsiloxyamodimethicone
Trimethylsiloxy silicate
Trisiloxane